



PRODUCT GUIDE

EXTRUDED ACRYLIC IN BRILLIANT CLARITY.







TABLE OF CONTENTS

CRYLON®	
■ At a glance	06 – 08
■ Technical Data Sheet	09 – 11
■ Sustainability	12 – 15
CRYLON® PRODUCT RANGE	
■ CRYLON®re	16 – 17
■ CRYLON® High Impact	18 – 19
■ CRYLON® HC	20 – 21
■ CRYLON® Soft Tone	22 – 23
■ CRYLON® SBW Sound Barrier Wall	24 – 25
CRYLON® APPLICATIONS	26 – 27



CRYLON®

CRYLON® comprises an extensive range of large-format, extruded acrylic glass sheets featuring outstanding clarity and first-rate optical characteristics, excellent colour rendering and varying degrees of transparency. Available in a range of clear, opals and opaques as well as selected colours and surface structures.

The premium quality surfaces have a high level of resistance to weathering and aging, and provide solutions for a variety of indoor and outdoor applications. CRYLON® is available in thicknesses from 1 to 25 mm.

Sustainable involvement and environmental protection have always been amongst the essential corporate objectives at 3A Composites. The minimisation of risks for man and environment as well as the reduction of environmental pollution through careful and efficient utilisation of resources is part of the corporate philosophy.

Our production site in Mainz, Germany is certified to DIN EN ISO 9001 for quality and to DIN EN ISO 50001 for energy. In addition, ongoing efforts are being made to reduce CO₂ emissions by scaling back energy and water consumption, increasing productivity and avoiding waste. Natural gas consumption, for instance, has been successfully reduced by more than 10 % since 2019.

The site is also participating in the programme Operation Clean Sweep® (OCS), which is dedicated to preventing plastic resin loss and to ensuring that this material does not end up in the environment.

CRYLON® sheets are subject to the highest quality standards and stringent monitoring. Our top priority is to ensure that CRYLON® sheets do not contain any hazardous substances. None of the raw materials used to produce CRYLON® sheets contain any heavy metals.

Read more about our commitment to sustainability starting on page 12.

[CRYLON® – EXTRUDED ACRYLIC IN BRILLIANT CLARITY.](#)

CRYLON®

EXTRUDED ACRYLIC IN BRILLIANT CLARITY.

CHARACTERISTICS

- Good optical properties
- Brilliant transparency
- Excellent colour rendering
- High-quality surfaces
- Very good weathering and ageing resistance
- Can be used in contact with foodstuff – meets all current European food control legislations
- Does not contain any toxic materials or heavy metals
- High impact grades (CRYLON® High Impact) for specific applications
- Easy to recycle
- Easy to fabricate
- Fire classification according to EN 13501-1 and UL94 HB for CRYLON® standard grades
- CRYLON® sheets are provided with a 10-year warranty

APPLICATION

- Displays (POS/POP)
- Signage | Lettering
- Corporate identity
- Shop design | Shop window decoration
- Interior design | Furniture
- Partitions | Cladding
- Lighting | Light boxes
- Illuminated advertising
- Glazing
- Food contact approved
- Sound barrier wall
- Construction business

PROCESSING

- Digital printing | Screen printing
- Laminating
- Painting | Spray painting | Lacquering
- Contour milling
- Laser cutting | Water jet cutting
- Sawing | Punching | Gluing | Drilling | Riveting | Screwing
- Thread cutting
- Folding (V-groove)
- Hot bending | Thermoforming
- Engraving | Polishing
- Tempering

For more details on the processing of CRYLON®, please contact our technical team.



CLEAR TRANSPARENT

Clear

 LT 92 %

WHITE OPAL/OPAQUE

<div></div> <div> White WO 075 OPAL LT 75 % </div>	<div></div> <div> White WO 047 OPAL LT 47 % </div>	<div></div> <div> White WO 035 OPAL LT 35 % </div>	<div></div> <div> White WO 026 OPAL LT 26 % </div>
<div></div> <div> White WO 025 OPAL LT 25 % </div>	<div></div> <div> White WS 025 OPAL LT 25 % </div>	<div></div> <div> White WO 004 OPAQUE LT 4 % </div>	<div></div> <div> White WL 053 LED OPAL LT 53 % </div>


COLOURS

<div></div> <div> Yellow 2450 LT 15 % </div>	<div></div> <div> Yellow 2470 LT 17 % </div>	<div></div> <div> Orange 2350 LT 5 % </div>	<div></div> <div> Red 2220 LT 4 % </div>
<div></div> <div> Red 2240 LT 3 % </div>	<div></div> <div> Blue 2650 LT 10 % </div>	<div></div> <div> Glossy Black 910 LT <1 % </div>	<div></div> <div> Brown LT 50 % </div>
<div></div> <div> Silicate Green LT 90 % </div>			

OPAQUE = non-transparent , OPAL = semi-transparent
 LT = Light transmission (Figures apply to 3 mm sheet thickness only. For the colours Brown and Silicate Green, the light transmission is constant over the entire thickness range, for the colour White WS 025 over the thickness range 2 – 6 mm.)
 The colours printed may vary from the original. To ensure exact colour matching please ask for a colour sample.

CRYLON® UVT

CRYLON® UVT is perfectly suitable for solariums and sunbeds. The sheets have high transmittance in the UV-A/UV-B spectral range and very good resistance to degradation following exposure to these rays.



CRYLON® Surface Structures

Besides the standard CRYLON® variants and the special products High Impact (page 17) and UVT, there is a variant available with a slight matt surface structure for a clear view without interfering light reflections (anti-reflective) as well as a patterned surface version (Prismatic – pyramid structure). They are particularly suitable for the areas glazing and decoration.



UVT = transparent to UV light
LT = Light transmission (Figures apply to 3 mm sheet thickness only.)
The colours printed may vary from the original. To ensure exact colour matching please ask for a colour sample.



PRODUCTS			CRYLON®
GENERAL			
Density	ISO 1183	kg/m³	1190
Water absorption against dry state (24h/23°C – 50x50x4 mm³)	ISO 62-1	%	0.2
Moulding shrinkage	ISO 294-4	%	0.5 – 0.8
Food contact – GHP	EU 10/2011	–	conform
Biocompatibility	ISO 10993-5	Classification	no cytotoxic
MECHANICAL			
Tensile modulus	ISO 527-2	MPa	3100
Tensile strength	ISO 527-2	MPa	70
Elongation at break	ISO 527-2	%	4
Flexural modulus	ISO 178	MPa	3000
Flexural strength	ISO 178	MPa	110
Impact strength Charpy, unnotched	ISO 179-1/1eU	kJ/m²	15
Impact strength Charpy, notched	ISO 179-1/1eA	kJ/m²	2
Ball indentation hardness	ISO 2039-1	MPa	235
OPTICAL			
Light transmission (3 mm)	ISO 13468-2	%	92
Refractive index n _D ²⁰	ISO 489	–	1.492
Haze	ISO 14782	%	< 1
Total solar energy transmission, g value (3 mm)	EN 410	%	86
Gloss value	DIN 67530	%	> 100
THERMAL			
Deflection temperature under load, DTUL (method A / B)	ISO 75-2	°C	95 / 100
VICAT temperature (Method B 50)	ISO 306	°C	105
Coefficient of linear thermal expansion	ISO 11359-2	mm/m x °C	0.07
Service temperature continuous use	–	°C	70
Service temperature at short term use	–	°C	90
Degradation temperature	–	°C	> 280
Forming temperature – air pressure – vacuum	–	°C	140 – 160 160 – 190
Specific heat capacity	ISO 11357-4	J/gK	1.47
Thermal conductivity	ISO 22007-1	W/mK	0.18
Fire resistance	EN 13501-1	Classification	E no burning droplets
	UL94	Classification	HB
ELECTRICAL			
Dielectric strength	IEC 60243-1	kV/mm	30
Electrical strength	IEC 60243-1	kV/mm	10
Volume resistivity	IEC 62631-3-1	Ω m	10 ¹³
Surface resistivity	IEC 62631-3-2	Ω	10 ¹⁵
Relative permittivity (1 MHz)	IEC 60250	–	2.7
Dielectric dissipation factor (1 MHz)	IEC 60250	–	0.02

Note: These technical data of our products are typical ones for CRYLON®. The actually measured values are subject to production variations.

PRODUCTS			CRYLON® HI 610	CRYLON® HI 620	CRYLON® HI 630
GENERAL					
Density	ISO 1183	kg/m³	1150	1160	1170
Water absorption against dry state (24h/23°C – 50x50x4 mm³)	ISO 62-1	%	0.3	0.3	0.25
Moulding shrinkage	ISO 294-4	%	0.6 – 0.9	0.6 – 0.9	0.6 – 0.9
Food contact – GHP	EU 10/2011	–	conform	conform	conform
Biocompatibility	ISO 10993-5	Classification	no cytotoxic	no cytotoxic	no cytotoxic
MECHANICAL					
Tensile modulus	ISO 527-2	MPa	1700	2200	2400
Tensile strength	ISO 527-2	MPa	40	50	55
Elongation at break	ISO 527-2	%	35	25	15
Flexural modulus	ISO 178	MPa	1700	2200	2400
Flexural strength	ISO 178	MPa	60	80	90
Impact strength Charpy, unnotched	ISO 179-1/1eU	kJ/m²	65	45	35
Impact strength Charpy, notched	ISO 179-1/1eA	kJ/m²	5	4	3
Ball indentation hardness	ISO 2039-1	MPa	100	135	155
OPTICAL					
Light transmission (3 mm)	ISO 13468-2	%	90	90	91
Refractive index n _D ²⁰	ISO 489	–	1.492	1.492	1.492
THERMAL					
VICAT temperature (Method B 50)	ISO 306	°C	98	102	104
Coefficient of linear thermal expansion	ISO 11359-2	mm/m x °C	0.11	0.10	0.09
Service temperature continuous use	–	°C	65	65	65
Service temperature at short term use	–	°C	75	80	85
Degradation temperature	–	°C	> 280	> 280	> 280
Forming temperature – air pressure – vacuum	–	°C	130 – 150 140 – 170	130 – 150 140 – 170	130 – 150 140 – 170
Specific heat capacity	ISO 11357-4	J/gK	1.5	1.5	1.5
Thermal conductivity	ISO 22007-1	W/mK	0.18	0.18	0.18
Fire resistance	UL94	Classification	HB	HB	HB
ELECTRICAL					
Dielectric strength	IEC 60243-1	kV/mm	30	30	30
Relative permittivity (1 MHz)	IEC 60250	–	2.9	2.9	2.9
Dielectric dissipation factor (1 MHz)	IEC 60250	–	0.03	0.03	0.03

Note: These technical data of our products are typical ones for CRYLON®.
The actually measured values are subject to production variations.

PRODUCTS			CRYLON® SOFT TONE	CRYLON® SBW
GENERAL				
Density	ISO 1183	kg/m³	1190	1190
Water absorption against dry state (24h/23°C – 50x50x4 mm³)	ISO 62-1	%	0.2	–
Moulding shrinkage	ISO 294-4	%	0.5 – 0.8	–
MECHANICAL				
Tensile modulus	ISO 527-2	MPa	3100	3100
Tensile strength	ISO 527-2	MPa	70	70
Elongation at break	ISO 527-2	%	4	–
Flexural modulus	ISO 178	MPa	3000	–
Flexural strength	ISO 178	MPa	110	–
Impact strength Charpy, unnotched	ISO 179-1/1eU	kJ/m²	15	–
Impact strength Charpy, notched	ISO 179-1/1eA	kJ/m²	2	–
OPTICAL				
Light transmission	ISO 13468-2	%	88 (3 mm)	> 90 (15 - 25 mm)
Refractive index n _D ²⁰	ISO 489	–	1.492	–
Gloss value	DIN 67530	%	< 35	–
THERMAL				
VICAT temperature (Method B 50)	ISO 306	°C	105	105
Coefficient of linear thermal expansion	ISO 11359-2	mm/m x °C	0.07	0.07
Service temperature continuous use	–	°C	70	70
Service temperature at short term use	–	°C	90	90
Degradation temperature	–	°C	> 280	> 280
Forming temperature – air pressure – vacuum	–	°C	140 – 160 160 – 190	140 – 160 –
Specific heat capacity	ISO 11357-4	J/gK	1.47	1.47
Thermal conductivity	ISO 22007-1	W/mK	0.19	0.18
Fire resistance	UL94	Classification	HB	–
ELECTRICAL				
Dielectric strength	IEC 60243-1	kV/mm	30	–
Electrical strength	IEC 60243-1	kV/mm	10	–
Volume resistivity	IEC 62631-3-1	Ω m	10 ¹³	–
Surface resistivity	IEC 62631-3-2	Ω	10 ¹⁵	–
Relative permittivity (1 MHz)	IEC 60250	–	2.7	–
Dielectric dissipation factor (1 MHz)	IEC 60250	–	0.02	–
SOUND BARRIER WALL				
Airborne sound insulation DL _R 15 – 25 mm	EN 1793-2:2013	dB		31 – 32 group B3
Absorbable windload 15 – 20 mm (2 m x 2 m) 20 – 25 mm (2 m x 3 m)	EN 1794-1:2011, Annex A	kN/m²	–	2.13 1.86
Stone impact resistance	EN 1794-1:2011, Annex C	–	–	requirements fulfilled
Fire resistance (undergrowth fire)	EN 1794-2:2011, Annex A	Classification	–	class 3


Note: These technical data of our products are typical ones for CRYLON®.
The actually measured values are subject to production variations.

SUSTAINABILITY

MISSION: TOGETHER. RESPONSIBLE.


Sustainability is at the core of everything we do. Our corporate ecological commitment is summed up by the **MISSION: TOGETHER. RESPONSIBLE.** As we also apply and comply with this mission in regard to our products, we have created a classification system. The five different categories in our **FIVE-DOT-MISSION** system indicate the factors with the greatest impact on sustainability. Our intention is to offer our partners guidance with their purchasing decision-making and to provide a transparent system. A system which focuses on the use of materials, the CO₂ content, the product life cycle and, of course, recycling, a topic of particular relevance for our products. Our FIVE-DOT-MISSION makes an assessment of a product on the basis of five categories and awards points per category, the product is then assigned to one of the five coloured DOTs. By this means we achieve a transparent, quick valuation logic which we can also use to gauge product innovation and improvement at 3A Composites.

THE FIVE-DOT CATEGORIES ARE:




1. BIOBASED CONTENT

Depending on the product, different raw materials are used to manufacture our panels. In this case, we look at the percentage of renewable raw materials used in our products. Our aim is to increase the percentage whenever possible and appropriate.




2. RECYCLED CONTENT

The industry selects recycled raw materials for use in the manufacture of new products which also fulfil requirements such as fire ratings, processing prerequisites and customer expectations in terms of functionality and appearance. This category is where we gauge the proportion of high quality recycled raw material in our products' total material input.




3. FOSSIL CO₂ BOUND IN THE MATERIAL

This category shows the weight of fossil CO₂ embedded in our panels. Differences here are principally due to the raw material type and origin, the density, the composition and the proportion of recycled content.



4. PRODUCT LIFE CYCLE

The plastic sheets and composite panels we produce are used by our customers for a longer period of time. In contrast to products used in the short term, these longer-term alternatives make an active contribution to saving resources. In this category we show our panels' average service life. Material properties result in disparities, so life cycles range from <1 year to even >30 years.



5. RECYCLABILITY


One of the most important aspects of sustainability is contributing to environmental protection by saving valuable raw materials and avoiding waste. Unlike the second category "recycled content", in this assessment category, we show options for recycling the panels after they have been in use. There are already, for instance, established recycling loops for paper and metals. At some production sites, the material can already be returned, so that material for new panels can be created from it. As a company, we came to the conclusion that thermal recycling does not seem sustainable enough, so it is not included in our FIVE-DOT classification. Instead, we are actively working with partner companies to establish a closed-loop, sustainable and future-oriented recycling economy.

As many as 3 points can be achieved in each of the categories presented, totalling a maximum of 15 points. According to the total number of points achieved (1-15), the FIVE-DOT classification is conducted using the following colour gradation.



Transparency is important to us! We will review the product assessment annually to see in which areas the product can be improved. We have set ourselves the goal of achieving the majority of our sales with products which achieve a rating of ≥ 7 points in the FIVE-DOT classification by 2030.

Join us on our sustainable mission!




SUSTAINABILITY

CRYLON® FIVE-DOT-MISSION


CRYLON® extruded acrylic glass sheets, offering brilliant clarity, have been assessed in line with the criteria described above. The products currently achieve a FIVE-DOT classification with a total of 7 respectively 10 points.




RECYCLED CONTENT


The current production of our CRYLON® acrylic sheets already contains a proportion of recycled PMMA material. The majority of this material is waste from the manufacturing process which, after being sorted into individual types, can be fed back into the production process as regrind to produce new CRYLON® sheets. We aim to continue increasing the proportion of recycled regrind in the product in the future. The recent introduction of CRYLON®re means we are now able to offer a product comprising at least 95% recycled material from PMMA sheet waste.

All raw materials used in our CRYLON® sheets comply with the requirements in the current version of the European Union's Chemicals Regulation (REACH). In particular, CRYLON® sheets are free of any of the substances listed in the current version of the ECHA Candidate List of Substances of Very High Concern (SVHC). PMMA does not contain any toxic substances or heavy metals which may cause environmental damage or pose risks to health.



FOSSIL CO₂ BOUND IN THE MATERIAL

Owing to the MMA used as a raw material in the manufacturing process, CRYLON® contains fossil carbon. However, thanks to its lower density, CRYLON® contains less fossil carbon per m² than other transparent plastics. As well as the lower density, another factor to note is that, compared with other plastics, the polymer molecule contains a lower percentage of carbon atoms. By using recycled PMMA in the production of CRYLON®re, the amount of new materials required can be significantly reduced. This makes a valuable contribution to lowering CO₂ emissions and avoiding waste.




PRODUCT LIFE CYCLE

Our CRYLON® acrylic glass sheets are made of extruded PMMA, a very robust, highly transparent and extremely durable material featuring excellent UV stability and resistance to weathering and ageing. We guarantee a service life of ten years for the CRYLON® product family. The sheets are protected against the harmful effects of ultra violet rays and there are no significant changes with regard to optical or mechanical properties. When processed, used, and cared for in an appropriate manner, the life cycle of our sheets can be considerably longer than ten years. An extended service life also leads to saving resources as fewer replacements are required. Our CRYLON® sheets are used in a wide variety of interior and exterior applications where priorities include durability, UV stability and, above all, transparency (92 % light transparency for colourless sheets). CRYLON® is a product offering sustainable, long-term use and excellent product performance.


RECYCLABILITY

CRYLON® sheets can be converted back into their original raw material, methyl methacrylate (MMA), using various recycling processes. Most modern recycling processes for extruded acrylic glass sheets use mechanical processes which, after sorting the material by type and grinding the PMMA sheets or waste material, feed the regrind back into manufacturing processes to produce new sheets. This is already being implemented in the production of our CRYLON®re sheets. In addition to mechanical recycling, the PMMA waste material can also be converted into an MMA liquid monomer using chemical recycling (through depolymerisation). The MMA recovered can then be reused to create, among other things, new PMMA sheets which comply with the highest quality standards. Renowned chemical companies are currently undertaking intensive research into improved depolymerisation technologies to achieve a more efficient and sustainable means of recovering the precious raw material MMA. For CRYLON® HC sheets, recycling by means of depolymerisation is recommended due to the abrasion-resistant coating on one or both sides.

CRYLON®re

EXTRUDED ACRYLIC SHEETS MADE FROM RECYCLED PMMA.

CRYLON®re are extruded acrylic sheets comprising at least 95% recycled material from PMMA sheet waste. Available in clear transparent as well as in black and white opaque versions, CRYLON®re comes in a range of different thicknesses and offers the same outstanding properties as extruded acrylic sheets manufactured conventionally. CRYLON®re features brilliant clarity with very good optical properties and excellent colour rendering. It is easy to process and its resistance to weathering and ageing is very good. CRYLON®re is the sustainable solution for a wide range of indoor and outdoor applications. The sheets are used, for instance, in high-class POS/POP displays, trade fair construction and also for shop counters and display cases.

CHARACTERISTICS



- Made from at least 95% recycled material from PMMA sheet waste
- Lighter than glass
- Good optical properties
- Very good resistance to weathering and ageing
- Easy to process
- For a wide range of interior and exterior applications

PROCESSING

- Digital printing | Screen printing
- Laminating
- Painting | Spray painting | Lacquering
- Contour milling
- Laser cutting | Water jet cutting
- Sawing | Punching | Gluing
- Drilling | Riveting | Screwing
- Thread cutting
- Folding (V-groove)
- Hot bending | Thermoforming
- Engraving
- Polishing
- Tempering

APPLICATION

- Displays (POS/POP)
- Signage | Lettering
- Corporate Identity
- Shop design | Shop window decoration
- Interior Design | Furniture
- Partitions | Cladding
- Lighting | Light boxes
- Glazing



LT = Light transmission (Figures apply to 3 mm sheet thickness only.)

CRYLON® HIGH IMPACT

ACRYLIC SHEETS WITH EXCELLENT IMPACT STRENGTH.

CRYLON® High Impact is the impact-modified product line in the CRYLON® family. It is especially robust, durable and weather-resistant. The three versions available – CRYLON® HI 610, CRYLON® HI 620 and CRYLON® HI 630 – feature outstanding optical and mechanical properties. CRYLON® HI is the first choice for a wide range of indoor and outdoor applications due to its wide operational range from approximately -20 °C to 65 °C. The impact-modified versions are characterised by a much higher resistance to stress cracking, in particular when exposed to chemicals.

CRYLON® High Impact sheets, like the standard CRYLON® version, are user-friendly and can be processed using all standard processing methods. In addition, the sheets can be formed at lower temperatures, which results in energy savings.

CRYLON® High Impact is available in transparent and opal versions.

CHARACTERISTICS





- Excellent impact strength
- Outstanding optical and mechanical properties
- Very good weathering and ageing resistance
- Does not contain any toxic materials or heavy metals
- Easy to handle, fabricate and form
- Fire classification according to UL94 HB
- For special applications

PROCESSING

- Digital printing | Screen printing
- Laminating
- Painting | Spray painting | Lacquering
- Contour milling
- Laser cutting | Water jet cutting
- Sawing | Punching | Gluing
- Drilling | Riveting | Screwing
- Thread cutting
- Folding (V-groove)
- Hot bending | Thermoforming
- Engraving
- Polishing
- Tempering

APPLICATION

- Displays (POS/POP)
- Signage | Lettering
- Shop design | Shop window decoration
- Partitions | Cladding
- Lighting | Light boxes
- Glazing

	Clear		White WO 026		Clear		Clear
	HI 610 LT 90 %		HI 610 LT 26 %		HI 620 LT 91 %		HI 630 LT 91 %

LT = Light transmission (Figures apply to 3 mm sheet thickness only.)



CRYLON® HC

EXTRUDED ACRYLIC SHEETS WITH INCREASED ABRASION RESISTANCE.

CRYLON® HC are extruded acrylic sheets with a one- or both sides abrasion resistant coating in brilliant transparency, which makes them especially suitable for flat applications. Thanks to this special hard coating, the sheets are less sensitive against scratches and have a high resistance to many chemicals and solvents.

CRYLON® HC is used for applications such as furniture construction (e.g. in the kitchen area), shop fitting and trade fair construction as well as for different kind of glazings – wherever an enhanced abrasion- and chemical resistance is required.

In terms of processing, CRYLON® HC can be used mostly in the same way as CRYLON® in its standard version. Due to the special surface coating, however, CRYLON® HC is not suitable for hot bending and thermoforming as well as for external applications.

CHARACTERISTICS


- Good optical properties
- Brilliant transparency
- Especially for flat applications
- Less sensitive against scratches;
high resistance to many chemicals and solvents

PROCESSING


- Digital printing | Screen printing
- Laminating
- Painting | Spray painting | Lacquering
- Contour milling
- Laser cutting | Water jet cutting
- Sawing
- Gluing
- Drilling | Screwing
- Thread cutting
- Engraving

APPLICATION

- Partitions | Cladding
- Glazing
- Construction business
- Interior design | Furniture construction
- Illuminated advertising



LT = Light transmission (Figures apply to 3 mm sheet thickness only.)



CRYLON® SOFT TONE

DOUBLE-SIDED MATT SURFACE.

CRYLON® Soft Tone is an extruded acrylic sheet with the appearance and feel of traditional frosted glass.

Due to its outstanding properties, CRYLON® Soft Tone provides a wide range of application possibilities for building and industrial glazing, decoration, lighting and advertising. Thanks to the double-sided matt surface of the material, images and text are to be seen clearly in all lighting conditions without distracting reflections.

Moreover, the relatively insensitive, easy to clean surface offers protection from scuffs, scratches and fingerprints.

CHARACTERISTICS



- Double-sided matt surface (single-sided matt on request)
- Improves light scatter
- Good optical properties
- Avoids reflective effects
- Stylish, trendy look
- Easy to maintain
- Very good weathering and ageing resistance
- Provided with a 10-year warranty
- Easy to handle, fabricate and form
- Does not contain any toxic materials or heavy metals
- Fire classification according to UL94 HB
- Stable thickness tolerances
- Overlengths available

PROCESSING

- Digital printing | Screen printing
- Laminating
- Painting | Spray painting | Lacquering
- Contour milling | Laser cutting | Water jet cutting
- Sawing | Punching | Gluing | Drilling | Screwing
- Thread cutting
- Folding (V-groove)
- Hot bending
- Thermoforming
- Engraving | Polishing
- Tempering

APPLICATION

- Signage | Lettering
- Shop design | Shop window decoration
- Partitions | Cladding
- Lighting | Light boxes
- Glazing

	Clear		White WO 075
	DOUBLE-SIDED MATT LT 88 %		DOUBLE-SIDED MATT LT 75 %

LT = Light transmission (Figures apply to 3 mm sheet thickness only.)

CRYLON® SBW SOUND BARRIER WALL

TRANSPARENT AND NOISE REDUCING

CRYLON® SBW Sound Barrier Wall is a sound absorbing material used in noise protection equipment on roads. Thanks to the optical properties and the very high transparency, it allows an unhindered view of the surroundings.

The advantages of using CRYLON® SBW in comparison with more traditional materials such as concrete are that it: is much more lightweight (allowing for easier construction); has a better optical view; avoids the creation of solid divisions; and is more aesthetically pleasing due to the range of colours and finishes available.

The CRYLON® SBW Soft Tone version features a matt surface, which is achieved by a special co-extruded coating on one or both sides. The satin matt finish on the surface avoids reflective effects, improves light scatter, and in so doing enhances the sound barrier's function.

CRYLON® SBW and its variations have been tested and approved according to the European standards EN 1793 and EN 1794 and correspond to the German regulatory ZTV-Lsw06. They comply with the requirements for noise insulation, fire performance, stability under wind load and stone cast resistance.

CHARACTERISTICS









- Excellent noise reduction
- High break-resistance
- Good optical properties
- Very high transparency
- Superior UV light resistance and outstanding weather resistance
- Easy to fabricate
- Mechanical stability
- Fire resistance according to DIN EN 1794-2
- Does not contain any toxic materials or heavy metals

PROCESSING

- Digital printing | Screen printing
- Laminating
- Contour milling
- Laser cutting | Water jet cutting
- Sawing | Drilling | Gluing | Thread cutting
- Hot bending
- Polishing | Tempering

APPLICATION

- Sound barrier wall devices
- Large scale glazing


	*Clear LT 90 %		*Blue 115 LT 44 %		*Blue 120 LT 50 %		*Green 110 LT 83 %
	*Green 036 LT 67 %		*Green 125 LT 56 %		*Brown 115 LT 45 %		*Grey 115 LT 7 %

* = Tested and certified in accordance with the requirements of EN 1793 and EN 1794 and approved for use in Sound Barrier Walls.

LT = Light transmission (Figures apply to 20 mm sheet thickness only.)

The colours printed may vary from the original. To ensure exact colour matching please ask for a colour sample.





GET INSPIRED:
WWW.DISPLAY.3ACOMPOSITES.COM/INSPIRATION



Polycasa N.V.
Van Doornelaan 2A | 2440 Geel, Belgium
www.display.3AComposites.com
A member of 3A Composites